

## Mirafi® 180N





Mirafi® 180N is a needlepunched nonwoven geotextile composed of polypropylene fibers, which are formed into a stable network such that the fibers retain their relative position. Mirafi® 180N is inert to biological degradation and resists naturally encountered chemicals, alkalis, and acids. Mirafi® 180N meets AASHTO M288-15 Class 1 for Elongation > 50%.

TenCate Geosynthetics Americas Laboratories are accredited by Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP). NTPEP Listed

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value		
-			MD	CD	
Grab Tensile Strength	ASTM D4632	lbs (N)	205 (912)	205 (912)	
Grab Tensile Elongation	ASTM D4632	%	50	50	
Trapezoid Tear Strength	ASTM D4533	lbs (N)	80 (356)	80 (356)	
CBR Puncture Strength	ASTM D6241	lbs (N)	500 (2224)		
			Maximum Opening Size		
Apparent Opening Size (AOS)	ASTM D4751	U.S. Sieve (mm)	80 (0.18)		
			Minimum I	Roll Value	
Permittivity	ASTM D4491	sec <sup>-1</sup>	1.4		
Flow Rate	ASTM D4491	gal/min/ft2 (l/min/m2)	95 (3870)		
			Minimum Test Value		
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	70		

Physical Properties	Unit	Roll Sizes	
Roll Dimensions (width x length)	ft (m)	12.5 x 360 (3.8 x 110)	15 x 300 (4.57 x 91.4)
Roll Area	yd² (m²)	500 (418)	

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

Mirafi® is a registered trademark of Nicolon Corporation.

Copyright © 2015 Nicolon Corporation. All Rights Reserved.

365 South Holland Drive Pendergrass, GA 30567 Tel 706 693 2226 Tel 888 795 0808 Fax 706 693 4400 www.tencate.com



